




Friction Material 956PN

Description

A moulded, asbestos free, copper reduced friction material containing carefully selected friction modifiers and randomly dispersed reinforcing fibres in a phenolic matrix.

Physical & Technical Properties

Specific Gravity	2,60 g/cm³	Min. Shear Strength	250 N/cm²
------------------	------------------------------	---------------------	-----------------------------



Operating Conditions

Max. Rubbing Pressure	P = 800 N/cm²	Max. Continuous Temperature	T = 350 °C
Max. Rubbing Speed	V = 30 m/s	Max. Short Term Temperature	T = 800 °C

Important Safety Note

This material is used on pads for different types and sizes of Air Actuated Disc Brakes. It is mandatory for safety reasons to comply with recommendations specific to each brake type regarding disc type, thickness and inspection, along with Disc Pad Replacement procedure, including brake adjustment and bedding.